

Dane Chemco

24 MIL

PROPERTY	UNIT		VALUES	TEST METHOD
Unit Weight	oz/yd ²		13.6	ASTM D3776
Warp Construction	Tapes/in	Warp	16	ASTM D3775
		Weft	18.3	
Tensile Grab Strength	lbf	Warp	371	ASTM D751
		Weft	486	
Tear Strength* [tongue]	lbf	Warp	74	ASTM D2261
		Weft	92	
Tear Strength [trapezoid]	lbf	Warp	67	ASTM D4533
		Weft	79	
Coating	mil	Black	4.1	ASTM D1777 MOD
		Black	4.1	
Mullen Burst Strength	psi	>	602	ASTM D751
1" Tensile Elongation	%		23.6	ASTM D882
Nominal Thickness	mil	Weft	24	ASTM D1777 MOD

*Includes force to shift tapes - Tear may be crosswise to direction of force.

Dane Chemco, Inc.
23770 Glasgow Place
Aurora, CO 80016
Office: 303 568-9273
Fax: 303 568-9277

Duane C. Petersen - Email
Betty Sue - Email

Colorado Sales/Distribution
911 Telluride Street
Aurora, CO 80011
Office: 720 859-0604
Fax: 720 859-3204

Chris Petersen - Email
Scott Petersen - Email

Fabrication Plant
97 4th Street N.W.
South Heart, ND 58655
Office: 701 677-5634
Fax: 701 677-5633

D. Kosteleyk - Email
Lisa Janke - Email